



Moist-Out MO-10™

A light spray lubricant, demoisurant and penetrant – formulated into one superior product. MO-10™ has excellent penetrating abilities that drive out moisture for quick, thorough moisture displacement, provides long-lasting lubrication, and protects from rust and corrosion.

Key Features & Benefits

- Quick moisture displacement
- Light, long-lasting lubrication
- Excellent penetrating action that creeps into hard-to-reach areas
- Loosens scale to free up sluggish or frozen mechanisms
- Protects from rust and corrosion
- Does not contain carbon tetrachloride
- Will not harm insulation or painted surfaces
- The better alternative to an aerosol can... the spray bottle is safer and full of product... no money wasted on hazardous ozone-depleting substances
- Contains **Muscle Metal Treatment MT-10®** technology for increased boundary film lubrication

Typical Applications

Demoisurant

- Distributor and plug wires • Wet or damp ignitions • Electrical circuits
- Motors • Controls • Starters • Relays
- Radios • Electronic equipment

Light Lubricant

- Locks • Hinges • Gears • Gear trains
- Levers • Linkages • Bearings • Cams
- Motors • Tools • Metal mechanisms
- Industrial equipment • Any other metal-to-metal moving or sliding surfaces

Corrosion Inhibitor

- Protects hinges, tools, locks, linkages,

levels, cams, gear trains, wheels, industrial equipment, and other metal mechanisms or sliding parts

- Protection from rust during long-term storage

Directions for Use

Remove as much excess moisture as possible before spraying **MO-10™**. After application, wipe away excess **MO-10™** with a clean, dry cloth. **WARNING! Never spray any demoisurant on a live circuit.** Serious shock or injury may occur.

Technical Data

Appearance.....	Green liquid
Odor.....	Mild petroleum, hint of maskant
Pour point.....	< - 49°F (- 45°C) D5950
Boiling point.....	> 450°F (232°C) D1120
Flash point.....	297°F (147°C) D93
Specific gravity @ 60°F, g/cm ³	0.9036 D1298
Lbs per gal (U.S.).....	~ 7.537
Viscosity @ 40F.....	12.229 cSt D445
Viscosity @ 100°C.....	2.746 cSt D445
Solubility.....	Insoluble (water)
Dielectric breakdown voltage.....	37.65 kV D877
Rust test, 4 hr.....	Pass (no rust) D665A

The above properties are typical values and do not constitute a product specification.

Container Availability

Item MO-10-16WS.....	16 oz. w/sprayer (473 mL)
Item MO-10-128.....	1 U.S. gallon (3.7 L)
Item MO-10-5G.....	5 U.S. gallon (18.9 L)
Item MO-10-55G.....	55 U.S. gallon (208 L)

